HFI/NQI 2010



Contribution ID: 144

Type: POSTER

Magnetism in CaFe2As2 and Phase Separation in Superconducting Ba0.5K0.5Fe2As2 and Sr0.5Na0.5Fe2As2 Single Crystals: A Mössbauer Study

abstract

Please specify whether you would prefer an oral or poster contribution.

poster

Summary

The ternary A1-xMxFe2As2 (A=Ca, Sr, Ba and Eu; M=K and Na) were found to have similar structural, magnetic and superconducting properties with the related RFeAsO1-xFx [1]. The Ca2Fe2As undergoes a first-order high-temperature h-T tetragonal to low-temperature l-T orthorhombic phase transition at TS^{*}170K [2]. Concomitant with the structural transition the Fe moments order in a commensurate AFM structure [3]. This compound becomes superconducting either under moderate applied pressure and or Na-doping [4,5]. The Ba0.5K0.5Fe2As2 and Sr0.5Na0.5Fe2As2 are superconductors with Tc ^{*}37 K and ^{*}35 K, respectively. ⊠SR measurements have shown a coexistence of superconductivity and phase separated static magnetic order in these compounds [6].

Mössbauer spectroscopy have been used to investigate the magnetic and structural phase transition of CaFe2As2 as well as the occurrence of phase separation in superconducting Ba0.5K0.5Fe2As2 and Sr0.5Na0.5Fe2As2 single crystals. A mosaic of single crystal plates, with the c axes parallel to ⊠-ray direction, were built to perform the Mössbauer transmission measurements. Room temperature measurements revealed that the main component of electric field gradient Vzz is along c axis for these ternary compounds. For the non superconducting a first-order magnetic transition. Low temperature spectra fits lead to Vzz >0 with Fe moments lying in the (a,b) plane. The quadrupole splitting ⊠EQ values have a discontinuity at ~170K confirming that structural and magnetic transition occurs concomitantly. The Mössbauer spectra of Ba0.5K0.5Fe2As2 and Sr0.5Na0.5Fe2As2 have a unique crystal site for Fe at room temperature, however at 4.2K the presence of two phases is clearly seen. For Ba0.5K0.5Fe2As2 ~ 51% of Fe is in a paramagnetic state while the remaining is in a magnetic phase with small magnetic moments (~0.15⊠B). For Sr0.5Na0.5Fe2As2 only ~12% of Fe are paramagnetic, the remaining Fe are in a magnetic state with magnetic moments of the order of ~0.57⊠B.

[1]C. Krellner, et al., Phys. Rev B 78 (2008)100504.

[2] N. Ni, et al., Phys. Rev. B 78 (2008) 014523.

[3] A. I. Goldman, et al., Phys. Rev B 78 (2008) 100506.

[4] M. S. Torikachvili, et al., Phys. Rev Lett. 101 (2008) 057006.

[5] P. M. Shirage, et al., Appl. Phys. Express 1 (2008) 081702.

[6] T. Goko, et al., Phys. Rev B 80 (2009) 024508.

Primary author: SANCHEZ, Dalber (Universidade Federal Fluminense)

Co-authors: BAGGIO-SAITOVITCH, Elisa (Centro Brasileiro de Pesquisas Fisicas. Rua Xavier Sigaud 150. Urca. CEP 22290-180. RJ, Brazil); CHENG, G. F. (Beijing National Laboratory for Condensed Matter Physics, Institute of Physics, Chinese Academy of Sciences, Beijing 100080, Peoples Republic of China); MUNEVAR, Julian (Centro Brasileiro de Pesquisas Fisicas. Rua Xavier Sigaud 150. Urca. CEP 22290-180. RJ, Brazil); ALZAMORA, Mariella (Centro Brasileiro de Pesquisas Fisicas. Rua Xavier Sigaud 150. Urca. CEP 22290-180. RJ, Brazil); CANFIELD, P. C. (3Ames Laboratory, U.S. DOE and Department of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, USA); BUDKO, Sergey (Ames Laboratory, U.S. DOE and Department of Physics and Astronomy, Iowa State University, Ames, Iowa 50011, USA)

Presenter: SANCHEZ, Dalber (Universidade Federal Fluminense)

Track Classification: Magnetism and Magnetic materials - Bulk and thin layers